

Textile Braided Medium Pressure Solvents And Paints Twin

Tekstil Örgülü Orta Basınç Dayanımlı İkiz Solvent Ve Boya



TUBE : SOLVENTS, PAINTS AND HYDRAULIC OILS RESISTANT POLYAMIDE.
REINFORCEMENT : HIGH TENSILE POLYESTER FIBER BRAID.
COVER : OIL, ABRASION AND WEATHER RESISTANT POLYURETHANE.
APPLICATION : FOR WATER BASED FLUIDS, SOLVENTS, PAINTS AND HYDRAULIC OILS AT MEDIUM PRESSURE.
FITTINGS : PRESSED OR REUSABLE.



SEELE : BESTÄNDIGER POLYAMID GEGEN HYDRAULIKÖL, SOLVENT UND FARBE.
EINLAGEN : HOCH REISSFESTES POLYESTERGEFLECHT.
DECKE : ÖL- UND WETTERBESTÄNDIGES, ABRIEFESTES POLYURETHAN.
ANWENDUNG : GEEIGNET FÜR MITTLEREN ARBEITSDRUCK BEI BE-UND ENTLADUNG VON SOLVENT, FARBEN, MINERALIEN, LUFT UND HYDRAULISCHEN ÖLEN.
EINBAUD : PRESSARMATUR UND SCHRAUBARMATUR.



SOTTOSTRATO : POLIAMMIDE RESISTENTE AI SOLVENTI, VERNICI ED OLII IDRAULICI.
RINFORZO : TRECCA IN POLIESTERE AD ALTA TENACITÀ.
COPERTURA : IN POLIURETANO ANTIABRASIONE, RESISTENTE ALL'OLIO ED AGLI AGENTI ATMOSFERICI.
IMPIEGO : PER FLUIDI A BASE ACQUOSA, SOLVENTI, VERNICI ED OLII SINTETICI A MEDIA PRESSIONE.
RACCORDI : PRESSATI O RECUPERABILI.



ALT KAT : SOLVENTLERE, BOYALARA VE HİDROLİK YAĞLARA DAYANIKLI POLİAMİD.
TAKVİYE : YÜKSEK MUKAVEMETLİ POLYESTER ÖRGÜ.
ÜST KAT : YAĞ, AŞINMA VE HAVA ŞARTLARINA DAYANIKLI POLİÜRETAN.
KULLANIM YERİ : ORTA BASINÇ DAYANIMI GEREKTİREN, SOLVENTLER, BOYALAR, HAVA, SU, MİNERAL VE HİDROLİK YAĞLARIN TAHLİYE İŞLERİNDE.
RAKORLAMA : SIKMA VEYA VİDALI.

ID/İÇ		OD/DÇ		WP/ÇB		BP/PB		BR/KY/r		W/A		L/B	
inch	mm	mm	mm	bar	psi	bar	psi	mm	mm	g/m	g/m	m	m
1/8"	3.2	7.2	7.2	150	2175	600	8700	30	30	80	80	+10	+10
5/32"	4.1	7.9	7.9	150	2175	600	8700	30	30	82	82	+10	+10
3/16"	5	8.3	8.3	150	2175	600	8700	35	35	88	88	+10	+10
1/4"	6.5	11.4	11.4	137	1987	548	7946	40	40	160	160	+10	+10
5/16"	8	13	13	137	1987	548	7946	50	50	190	190	+10	+10
3/8"	9.7	15.5	15.5	137	1987	548	7946	65	65	260	260	+10	+10
1/2"	13	18.6	18.6	125	1813	500	7250	80	80	292	292	+10	+10
5/8"	16.5	22.7	22.7	100	1450	400	5800	100	100	462	462	+10	+10
3/4"	19.5	25.5	25.5	87	1262	348	5046	130	130	554	554	+10	+10
1"	25	32.6	32.6	75	1088	300	4350	160	160	840	840	+10	+10



-40°C / +100°C
-40°F / +212°F

(For transfer of water based fluids and air max +65 °C / 149 °F)
(Beim Transport von Wasser und Luft enthaltenden Flüssigkeiten max. 65 °C / 149 °F)
(Per conduzione di fluidi a base acquosa ed aria max +65 °C / 149 °F)
(İçinden geçen hava ve su bazlı akışkanlar için en yüksek +65 °C / 149 °F)

Possible applications:

Anwendungsbeispiele:

Esempi d' applicazione:

Bazı kullanım yeri örnekleri:



NORMS NORMEN NORME NORMLAR		MARKING BESCHRIFTUNG MARCATURA MARKALAMA	INK JET	COLOUR FARBEN COLORI RENKLER	 
-------------------------------------	--	---	---------	---------------------------------------	---