

Steel Reinforced Very High Pressure Solvents And Paints Çelik Tel Örgülü Çok Yüksek Basınç Dayanımlı Solvent Ve Boya



	TUBE REINFORCEMENT COVER APPLICATION FITTINGS	: SOLVENTS, PAINTS AND HYDRAULIC OILS RESISTANT POLYAMIDE. : HIGH TENSILE 2 STEEL WIRE BRAIDS. : OIL, ABRASION AND WEATHER RESISTANT POLYURETHANE. : FOR WATER BASED FLUIDS, SOLVENTS, PAINTS AND HYDRAULIC OILS AT VERY HIGH PRESSURE. : PRESSED.
	SEELE EINLAGEN DECKE ANWENDUNG EINBAND	: BESTÄNDIGER POLYAMID GEGEN HYDRAULIK ÖL, SOLVENT UND FARBE. : HOCH REISSFESTES DOPPELTES STAHLDRACHTGEFLECHT. : ÖL- UND WETTERBESTÄNDIGES, ABRIEBFESTES POLYURETHAN. : GEEIGNET FÜR SEHR HOHEN ARBEITS DRUCK BEI BE- UND ENTLADUNG VON SOLVENT, FARBEN, MINERALIEN, LUFT UND HYDRAULISCHEN ÖLEN. : PRESSARMATUR.
	SOTTOSTRATO RINFORZO COPERTURA IMPIEGO RACCORDI	: POLIAMMIDE RESISTENTE AI SOLVENTI, VERNICI ED OLII IDRAULICI. : 2 TRECCE IN ACCIAIO AD ALTA TENACITÀ. : IN POLIURETANO ANTIABRASIONE, RESISTENTE ALL'OLIO ED AGLI AGENTI ATMOSFERICI. : PER FLUIDI A BASE ACQUOSA, SOLVENTI, VERNICI ED OLII SINTETICI A PRESSIONE ALTISSIMA. : PRESSATI.
	ALT KAT TAKVİYE ÜST KAT KULLANIM YERİ RAKORLAMA	: SOLVENTLERE, BOYALARA VE HİDROLİK YAĞLARA DAYANIKLI POLİAMİD. : YÜKSEK MUKAVEMETLİ İKİ KAT ÇELİK TEL ÖRGÜ. : YAĞ, AŞINMA VE HAVA ŞARTLARINA DAYANIKLI POLİÜRETAN. : ÇOK YÜKSEK BASINÇ DAYANIMI GEREKTİREN, SOLVENTLER, BOYALAR, HAVA, SU, MİNERAL VE HİDROLİK YAĞLARIN TAHLİYE İŞLERİNDE. : SIKMA.

ID/İÇ		OD/DÇ		WP/ÇB		BP/PB		BR/KY/r		W/A		L/B	
inch	mm	mm	bar	psi	bar	psi	mm	g/m	m				
1/8"	3.2	9.8	450	6525	1800	26100	30	172	+10				
5/32"	4.1	10.5	400	5800	1600	23200	30	195	+10				
3/16"	5	11.3	390	5655	1560	22620	35	238	+10				
1/4"	6.5	13	390	5655	1560	22620	40	274	+10				
5/16"	8	15	330	4785	1320	19140	50	312	+10				
3/8"	9.7	17	315	4568	1260	18270	60	424	+10				
1/2"	13	20	275	3988	1100	15950	80	463	+10				
5/8"	16.5	23.5	195	2828	780	11310	115	574	+10				
3/4"	19.5	28	180	2610	720	10440	160	611	+10				
1"	25	34	160	2320	640	9280	200	760	+10				



-40°C / +100°C
-40°F / +212°F


(For transfer of water based fluids and air max +65 °C / 149 °F)
(Beim Transport von Wasser und Luft enthaltenden Flüssigkeiten max. 65 °C / 149 °F)
(Per conduzione di fluidi a base acquosa ed aria max +65 °C / 149 °F)
(İçinden geçen hava ve su bazlı akışkanlar için en yüksek +65 °C / 149 °F)

Possible applications:

Anwendungsbeispiele:

Esempi d' applicazione:

Bazı kullanım yeri örnekleri:



NORMS NORMEN NORME NORMLAR		MARKING BESCHRIFTUNG MARCATURA MARKALAMA	INK JET	COLOUR FARBEN COLORI RENKLER		
-------------------------------------	--	---	---------	---------------------------------------	--	--